




-50 m

Hydro stoll		average		
Length of ore	Analysed samples	P ₂ O ₅	Nb ₂ O ₅	CaCO ₃
56.89 m.	33	2.96%	0.206%	63.8%

Söve, Hydro Deposit
Profile Grunnstoll

-100 m