


8481

| | linse I | linse II | linse III |
|---------------|--|---|---|
| +220 d 191 | 1.80m: 3.40% Zn 1.09Pb; 0.48Cu; 5.61S | | |
| | 0.55m: 11.06% Zn 3.88Pb; 0.23Cu; 15.93S | | |
| +200 d 190 | 1.00m: 4.92% Zn 0.58Pb; 0.15Cu; 9.78S | | |
| C 8 | | 5.75m: 8.77% Zn 0.22Pb; 0.35Cu | 3.00m: 13.73% Zn 0.57Pb 1.00m: 0.80Cu |
| +180 N | | 2.00m: 8.28% Zn 0.18Pb; 0.15Cu | |
| d 88 | | 6.15m: 6.54% Zn 0.10Pb; 0.60Cu | |
| | | 5.70m: 4.30% Zn 0.53Pb; 0.38Cu; 7.43S | |
| +160 d 90 | | 2.81m: 6.04% Zn 0.92Pb; 0.47Cu; 14.07S | |



Profil 340 Øst
M=1:500

13/6 -61
8/6 -61
A.V. 2/11 -61