



8511

	linse I	linse II	linse III	
d 123	0,50m malmslager			+220
d 126	0,50m: 5,69% Zn, 4,26% Cu; 12,91% S			+200
d 124	0,20m: 5,80% Zn 0,55% Pb; 0,69% Cu; 13,07% S			+180
d 250	5,50m: 1,40% Zn 0,15% Pb; 0,44% Cu; 5,34% S			+160
d 251	4,00m: 1,61% Zn 0,60% Pb; 0,53% Cu; 6,47% S			+140

x=400

y=42.374

No 12519  
 Profil 960 Øst  
 M=1:500  
 23/8-61  
 A. K. 8/2-65