



853

	linse I	linse II	linse III	
d 81		15.82 m: 4.01% Zn 0.72 Pb; 0.68 Cu; 3.73 S		boret eller fallet!
d 84	1.74 m: 6.75% Zn 0.46 Pb; 0.37 Cu; 1.00 S	1.58 m: 5.04% Zn 1.31 Pb; 0.33 Cu; 12.30 S		muldrens +180 6.5 m: 4.42% Zn 0.58 Pb; 0.19 Cu; 12.40 S
d 83		3.04 m: 4.02% Zn 0.65 Pb; 0.44 Cu; 7.70 S		
		3.41 m: 2.36% Zn 0.31 Pb; 0.54 Cu; 11.83 S		
		3.07 m: 10.18% Zn 3.69 Pb; 0.41 Cu; 9.65 S		+160
d 80		4.27 m: 3.48% Zn 0.77 Pb; 0.76 Cu; 9.24 S		
d 79		3.14 m: 3.88% Zn 1.02 Pb; 0.44 Cu; 8.58 S	1.06 m impr + 1.09 m: 3.31% Zn 0.31 Pb; 0.18 Cu; 5.26 S	+140
		1.00 m: 4.36% Zn 0.15 Pb; 0.11 Cu; 9.15 S		
d 82		1.48 m: 19.46% Zn 2.68 Pb; 0.25 Cu; 12.73 S		
		0.36 m: 7.33% Zn 1.43 Pb; 0.26 Cu; 10.38 S		
		0.31 m: 7.02% Zn 0.66 Pb; 0.27 Cu; 9.98 S		+120

26/8-61
 Profil 980 Øst
 M=1:500
 1:200
 20/8
 A x 22/10-60