

476: 0.00-1.60m: 0.72% Pb, 0.31% Cu, 2.18% Zn
 477: 0.00-4.65m: 0.75% Pb, 0.34% Cu, 2.31% Zn
 478: 0.00-13.45m: 0.69% Pb, 0.84% Cu, 2.95% Zn
 482: 0.00-23.60m: 1.45% Pb, 0.41% Cu, 4.93% Zn
 483: 0.00-30.30m: 1.41% Pb, 0.39% Cu, 5.37% Zn

1: 0.56 m²
 2: 0.80 m² } 0.86 m²
 3: 0.93 m²
 4: 1.78 m² } 2.71 m²
 5: 4.37 m²
 6: 10.20 m² } 14.57 m²
 7: 18.88 m²
 8: 26.40 m² } 45.28 m²
 9: 36.36 m²
 10: 50.40 m² } 86.76 m²
 Σ 150.18 m²

-20

-20

-40


-40

-60

-60

-80

-80




VEIET GJENNOMSNITTANALYSE, GJENNOMFØRSEL:

$$Pb: \frac{0.72 \cdot 0.86 + 0.75 \cdot 2.71 + 0.69 \cdot 14.57 + 1.45 \cdot 45.28 + 1.41 \cdot 86.76}{150.18} = 1.34\%$$

$$Cu: \frac{0.31 \cdot 0.86 + 0.34 \cdot 2.71 + 0.84 \cdot 14.57 + 0.41 \cdot 45.28 + 0.39 \cdot 86.76}{150.18} = 0.44\%$$

$$Zn: \frac{2.18 \cdot 0.86 + 2.31 \cdot 2.71 + 2.95 \cdot 14.57 + 4.93 \cdot 45.28 + 5.37 \cdot 86.76}{150.18} = 4.93\%$$



9232

dårlig (impregnasjons-) malm < 2% Zn
 middels (stripet) malm 2-3% Zn
 god (stripet) malm 3-4% Zn
 meget god malm > 4% Zn

X 925 440

420

400

380

360

MOFJELLET GRUBER	M = 1: 200	TEGN	
		TRAC	
Y 43 400	KÅRT NR.	KFR	
		REY	
	ARKIV NR.		

-80

-80